Range: HYGIENE





IMAGE ANATOMIC

ERGONOMIC AND MORE ENVIRONMENTALLY FRIENDLY

Ref: 0183

DESCRIPTION

Anatomical insoles "IMAGE" more ergonic and more environmentally friendly and always treated with S3F®

KEYS FEATURES

- > Anatomical
- > Ultra-strong and absorbent capacity
- > Anti odor
- > PU foam made of 80% recycled materials

FIELD OF USE

· All work and activity sector

WORKING ENVIRONMENT

· All environment

COMPATIBILITY

· All safety shoes and boots

BENEFITS

CHARACTERISTICS

· Polyester felt for comfort and a good abrasion resistance

· Anatomical insole with foot arch and heel cup

· Resistance to abrasion

· Exclusive S3F® treatment*

- · Prevents the development of odours and the growth of bacteria and fungi responsible for fungal infections*.
- · Anti-slip





Size AG: 36/37 to 48/49

Standards

- · EN 12746
- · EN 13520





DOWNLOADING

OF PRODUCT DATASHEETS AND **DOCUMENTS ON WEBSITE** www.jlf-pro.com



IMAGE ANATOMIC - REF: 0183

COMPOSITION / MATERIAL

- · 100% polyester felt fabric
- · PU foam made of 80% recycled materials
- · Conductive sewing thread made of continuous multifilament yarn polyamide (80%) polyester-stainless steel(20%)
- · *Contain biocide : Dimethyloctadecyl[3-(trimethoxysilyl)propyl]ammonium chloride

USE / CARE INSTRUCTIONS & ADVICES

- · Place the green textile side in contact with the foot
- \cdot For best performance and efficiency, we recommend removing your insoles from your shoes every evening to dry them.
- · The insole is not washable (treated insole)

LIFESPAN

3 months

The efficiency of the treatment may change more or less depending on criteria such as intensity of the sudoral flow, the nature of the shoe articles, the body hygiene,...

S3F® TREATMENT

- Effective on the foot in up to 95% of cases on fungi and up to 99% of cases on nail fungi. (Trichophyton rubrum, Trichophyton mentagrophytes, Candida parapsilosis)
- Effective on the foot on most bacteria causing unpleasant foot odour. (Staphylococcus aureus, Staphylococcus epidermidis, Corynebacterium minutissimum, brevibacterium epidermidis, Propionibacterium granulosum)

LAB TESTS RESULTS			
STANDARD	NORMATIVE REFERENCE	TESTING	RESULTS
Water absorption : Water desorption :	FN 17746	Absorption power : Desorption % of water after 16 hours :	225 mg/cm² 100%
Resistance to abrasion	EN 13520	Cycles to produce a hole > Dry test > Wet test	>25 600 >18 800
Antistatic behavior	20344 §5.10	After conditioning in dry environment > left foot > right foot (tested with antistatic shoes left foot = 50 Mohms and rigth foot = 13 Mohms) After conditioning in wet environment > left foot > right foot (tested with antistatic shoes left foot = 3,2 Mohms and rigth foot = 1,7 Mohms)	56,0 Mohms 14,0 Mohms 3,2 Mohms 1,8 Mohms

Creation Date:

01/12/2020-V1

NOT CONCERNED

Revision Date:







Label awarded according to specifications derived from the ISO 26 000 standard and audited annually by Ecocert Environnement

