



## CUT IMAGE



©JLFF Pro

Ref: 0282

FABRICATION  
FRANÇAISE

### DESCRIPTION

Hygiene insole treated with S3F® to cut to fit to all shoe sizes.

### KEYS FEATURES

- > Ultra-strong
- > Absorbent
- > Anti-odour

### FIELD OF USE

- All work and activity sector

### WORKING ENVIRONMENT

- All environment

### COMPATIBILITY

- All safety shoes and boots

### CHARACTERISTICS

- Green comfort needle punched fabric with polyviscose and a binding providing long-term resistance to abrasion.
- Under-layer in latex foam with active carbon and anti-static
- Exclusive S3F® treatment
- Antistatic

### BENEFITS

- Prevents the development of odours and the growth of bacteria and fungi responsible for fungal infections\*
- Anti-slip
- Resistance to abrasion
- Can be cut to your shoe size

#### Size

Multisize to cut from 35 to 46

#### Standards

- EN 12746
- EN 13520
- 20344 §5.10



### COMPLEMENTARY PRODUCTS



0368-FRAICHEUR



0610-DESINFECTANT DESODORISANT



CUT IMAGE - REF : 0282

### COMPOSITION / MATERIAL

- Green non-woven textile made of a 65% polyester, 35% viscose with binder and biocide treatment\*.
- Activated carbon latex foam under-layer with biocide\* and antistatic treatment
- Antistatic treatment
- \*Contains biocides : Octhilinone (ISO) and Zinc pyrithione

### LIFESPAN

3 months because of the treatment

The efficiency of the treatment may change more or less depending on criteria such as intensity of the sudoral flow, the nature of the shoe articles, the body hygiene,...

### S3F® TREATMENT

- Effective on the foot on most bacteria causing unpleasant foot odour. (Staphylococcus aureus, Staphylococcus epidermidis, Corynebacterium minutissimum, brevibacterium epidermidis, Propionibacterium granulosum)
- Effective on the foot in up to 95% of cases of fungi and up to 99% of cases of nail fungi. (Trichophyton rubrum, Trichophyton mentagrophytes, Candida parapsilosis)

### USE / CARE

#### INSTRUCTIONS & ADVICES

- Place the textile side in contact with the foot.
- For best performance and efficiency, we recommend removing your insoles from your shoes every evening to dry them.
- Non-washable insole (treated insole)

### LAB TESTS RESULTS

STANDARD	NORMATIVE REFERENCE	TESTING	RESULTS
Water absorption : Water desorption :	EN 12746	Absorption power : Desorption % of water after 16 hours :	171 mg/cm <sup>2</sup> 95,16%
Resistance to abrasion	EN 13520	Cycles to produce a hole > Dry test > Wet test	> 100 000 > 44 800
Antistatic behaviour	20344 §5.10	> Electrical resistance after conditioning in dry atmosphere > Electrical resistance after conditioning in wet atmosphere	> Compliant > Compliant

Creation Date :  
01/11/2020-V1

Revision Date :  
NOT CONCERNED



Label awarded according to specifications derived from the ISO 26 000 standard and audited annually by Ecocert Environnement



GROUPE JLF - 4 rue du Président Carnot - 69002 Lyon – France - Tél. +33 (0)4 78 37 07 37 – Fax. +33 (0)4 78 37 62 89  
SAS CAPITAL 361 760 € - RCS ANGOULEME B 314284134 - CODE APE 1520Z - CODE TVA FR 95 314 284 134 - N°SIRET 314 284 134 00041

GROUPE JLF reserves the right to modify the manufacturing characteristics of the product. Non contractual document